



Standard Specification for Steel Castings, Martensitic Stainless and Alloy, for Pressure-Containing Parts, Suitable for High-Temperature Service¹

This standard is issued under the fixed designation A217/A217M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification² covers martensitic stainless steel and alloy steel castings for valves, flanges, fittings, and other pressure-containing parts (**Note 1**) intended primarily for high-temperature and corrosive service (**Note 2**).

1.2 One grade of martensitic stainless steel and nine grades of ferritic alloy steel are covered. Selection will depend on design and service conditions, mechanical properties, and the high-temperature and corrosion-resistant characteristics (**Note 3**).

NOTE 1—Carbon steel castings for pressure-containing parts are covered by Specification **A216/A216M**. Low alloy quench-and-tempered grades equivalent to Specification A217/A217M grades may be found in both Specifications **A352/A352M** and **A487/A487M**.

NOTE 2—The grades covered by this specification represent materials that are generally suitable for assembly with other castings or wrought steel parts by fusion welding. It is not intended to imply that these grades possess equal degrees of weldability; therefore, it is the responsibility of the purchaser to establish for himself a suitable welding technique. Since these grades possess varying degrees of suitability for high-temperature and corrosion-resistant service, it is also the responsibility of the purchaser to determine which grade shall be furnished, due consideration being given to the requirements of the applicable construction codes.

NOTE 3—The committee formulating this specification has included nine grades of materials that are considered to represent basic types of ferritic alloy steels suitable for valves, flanges, fittings, and other pressure-containing parts. Additional alloy steels that may better fulfill certain types of service will be considered for inclusion in this specification by the committee as the need becomes apparent.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in

each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

2.1 *ASTM Standards*:³

A216/A216M Specification for Steel Castings, Carbon, Suitable for Fusion Welding, for High-Temperature Service

A352/A352M Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service

A487/A487M Specification for Steel Castings Suitable for Pressure Service

A488/A488M Practice for Steel Castings, Welding, Qualifications of Procedures and Personnel

A703/A703M Specification for Steel Castings, General Requirements, for Pressure-Containing Parts

A802/A802M Practice for Steel Castings, Surface Acceptance Standards, Visual Examination

A985/A985M Specification for Steel Investment Castings General Requirements, for Pressure-Containing Parts

E165 Practice for Liquid Penetrant Examination for General Industry

E709 Guide for Magnetic Particle Testing

3. General Conditions for Delivery

3.1 Except for investment castings, castings furnished to this specification shall conform to the requirements of Specification **A703/A703M** including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification **A703/**

¹ This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.18** on Castings.

Current edition approved May 1, 2010. Published June 2010. Originally approved in 1939. Last previous edition approved in 2008 as A217/A217M – 08. DOI: 10.1520/A0217_A0217M-10.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-217/SA 217M in Section II of that code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

A703M constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A703/A703M**, this specification shall prevail.

3.2 Steel investment castings furnished to this specification shall conform to the requirements of Specification **A985/A985M**, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification **A985/A985M** constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A985/A985M**, Specification **A985/A985M** shall prevail.

4. Ordering Information

4.1 The inquiry and order should include or indicate the following:

4.1.1 A description of the casting by pattern number or drawing (dimensional tolerances shall be included on the casting drawing),

4.1.2 Grade of steel,

4.1.3 Options in the specification,

4.1.4 Whether the castings are to be produced using the investment casting process, and

4.1.5 The supplementary requirements desired including the standards of acceptance.

5. Heat Treatment

5.1 All castings shall receive a heat treatment proper to their design and chemical composition.

5.2 Castings shall be furnished in the normalized and tempered conditions; Grades WC1, WC4, WC5, WC6, and CA15 shall be tempered at 1100°F [595°C] min; Grades WC9, C5, C12, and WC11 shall be tempered at 1250°F [675°C] min; Grade C12A shall be normalized at 1900-1975°F [1040-1080°C] and tempered at 1350-1470°F [730-800°C].

5.3 Heat treatment shall be performed after castings have been allowed to cool below the transformation range.

6. Chemical Composition

6.1 The steel shall be in accordance with the requirements as to chemical composition prescribed in **Table 1** (**Note 4**).

NOTE 4—The role of alloying elements in the development of Grade C12A has been extensively investigated. V and Cb contribute to precipitation strengthening by forming fine and coherent precipitation of M(C,N)X carbo-nitrides in the ferrite matrix. V also precipitates as VN during tempering or during creep. The two elements are more effective in combination. Therefore, the addition of strong nitride-forming elements, those with a stronger affinity for nitrogen than Cb and V, as deoxidation agents, interferes with these high-temperature strengthening mechanisms.⁴

7. Tensile Requirements Tensile Requirements

7.1 Steel used for the castings shall be in accordance with the requirements as to tensile properties prescribed in **Table 2**.

⁴ Viswanathan, R. and Bakker, W. T., *Materials for Ultra Supercritical Fossil Power Plants*, EPRI, Palo Alto, CA, 2000. TR-114750.

TABLE 1 Chemical Requirements

NOTE—All values are maximum unless otherwise indicated.

	Composition, %									
	Carbon Molybdenum	Nickel Chromium Molybdenum	Nickel Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum Vanadium	Chromium
Grade Identification Symbol	WC1	WC4	WC5	WC6	WC9	WC11	C5	C12	C12A	CA15
UNS Number	J12524	J12082	J22000	J12072	J21890	J11872	J42045	J82090	J84090	J91150
Carbon	0.25	0.05–0.20	0.05–0.20	0.05–0.20	0.05–0.18	0.15–0.21	0.20	0.20	0.08–0.12	0.15
Manganese	0.50–0.80	0.50–0.80	0.40–0.70	0.50–0.80	0.40–0.70	0.50–0.80	0.40–0.70	0.35–0.65	0.30–0.60	1.00
Phosphorus	0.04	0.04	0.04	0.04	0.04	0.020	0.04	0.04	0.030	0.040
Sulfur	0.045	0.045	0.045	0.045	0.045	0.015	0.045	0.045	0.010	0.040
Silicon	0.60	0.60	0.60	0.60	0.60	0.30–0.60	0.75	1.00	0.20–0.50	1.50
Nickel	...	0.70–1.10	0.60–1.00	0.40	1.00
Chromium	...	0.50–0.80	0.50–0.90	1.00–1.50	2.00–2.75	1.00–1.50	4.00–6.50	8.00–10.00	8.0–9.5	11.5–14.0
Molybdenum	0.45–0.65	0.45–0.65	0.90–1.20	0.45–0.65	0.90–1.20	0.45–0.65	0.45–0.65	0.90–1.20	0.85–1.05	0.50
Columbium	0.03	0.060–0.10	...
Nitrogen	0.030–0.070	...
Vanadium	0.06	0.18–0.25	...
Specified Residual Elements										
Aluminum	0.01	0.02	...
Copper	0.50	0.50	0.50	0.50	0.50	0.35	0.50	0.50
Nickel	0.50	0.50	0.50	0.50	0.50	0.50
Chromium	0.35
Titanium	0.01	...
Tungsten	0.10	0.10	0.10	0.10	0.10	...	0.10	0.10
Vanadium	0.03
Zirconium	0.01	...
Total content of these residual elements	1.00	0.60	0.60	1.00	1.00	1.00	1.00	1.00

TABLE 2 Tensile Requirements

Grade	Tensile Strength, ksi [MPa]	Yield Strength, ^A min, ksi [MPa]	Elongation in 2 in. [50 mm] min, % ^B	Reduction of Area, min, %
WC1	65 [450] to 90 [620]	35 [240]	24	35
WC4, WC5, WC6, WC9	70 [485] to 95 [655]	40 [275]	20	35
WC11	80 [550] to 105 [725]	50 [345]	18	45
C5, C12	90 [620] to 115 [795]	60 [415]	18	35
C12A	85 [585] to 110 [760]	60 [415]	18	45
CA15	90 [620] to 115 [795]	65 [450]	18	30

^A Determine by either 0.2 % offset method or 0.5 % extension-under-load method.

^B When ICI test bars are used in tensile testing as provided for in Specification **A703/A703M**, the gage length to reduced section diameter ratio shall be 4 to 1.

8. Quality

8.1 The surface of the casting shall be examined visually and shall be free of adhering sand, scale, cracks, and hot tears. Other surface discontinuities shall meet the visual acceptance standards specified in the order. Practice **A802/A802M** or other visual standards may be used to define acceptable surface discontinuities and finish. Unacceptable visual surface discontinuities shall be removed and their removal verified by visual examination of the resultant cavities. When methods involving high temperature are used in the removal of discontinuities, castings shall be preheated to at least the minimum temperatures in **Table 3**.

8.2 When additional inspection is desired, Supplementary Requirements S4, S5, and S10 may be ordered.

8.3 The castings shall not be peened, plugged, or impregnated to stop leaks.

9. Repair by Welding

9.1 Repairs shall be made using procedures and welders qualified under Practice **A488/A488M**.

9.2 Weld repaired Grade C12A castings shall be post-weld heat treated at 1350-1470°F [730-800°C].

TABLE 3 Minimum Preheat Temperatures

Grade	Thickness, in. [mm]	Minimum Preheat Temperature, °F [°C]
WC1	5/8 and under	50 [10]
	Over 5/8 [15.9]	250 [120]
WC4	All	300 [150]
WC5	All	300 [150]
WC6	All	300 [150]
WC9	All	400 [200]
WC11	All	300 [150]
C5	All	400 [200]
C12	All	400 [200]
C12A	All	400 [200]
CA15	All	400 [200]

9.3 Weld repairs shall be inspected to the same quality standards that are used to inspect the castings. When castings are produced with Supplementary Requirement S4 specified, weld repairs shall be inspected by magnetic particle examination to the same standards that are used to inspect the castings. When castings are produced with Supplementary Requirement S5 specified, weld repairs on castings that have leaked on hydrostatic test, or on castings in which the depth of any cavity prepared for repair welding exceeds 20 % of the wall thickness or 1 in. [25 mm], whichever is smaller, or on castings in which any cavity prepared for welding is greater than approximately 10 in.² [65 cm²], shall be radiographed to the same standards that are used to inspect the castings.

9.4 Weld repairs shall be considered major in the case of a casting that has leaked on hydrostatic test, or when the depth of the cavity prepared for welding exceeds 20 % of the wall thickness or 1 in. [25 mm], whichever is smaller, or when the extent of the cavity exceeds approximately 10 in.² [65 cm²]. All castings with major repair welds shall be thermally stress relieved or completely reheat-treated. This mandatory stress relief or reheat-treatment shall be in accordance with the qualified procedure used. Major repairs shall be inspected to the same quality standards that are used to inspect the castings.

10. Keywords

10.1 alloy steel; high temperature; martensitic stainless steel; pressure containing; steel castings

SUPPLEMENTARY REQUIREMENTS

The following supplementary requirements shall not apply unless specified in the purchase order. Lists of standardized supplementary requirements for use at the option of the purchaser are included in Specifications **A703/A703M** and **A985/A985M**. Those which are ordinarily considered suitable for use with this specification are given below. Others enumerated in Specifications **A703/A703M** and **A985/A985M** may be used with this specification upon agreement between the manufacturer and purchaser.

S1. Unspecified Elements
S2. Destruction Tests
S3. Bend Tests
S4. Magnetic Particle Inspection
S5. Radiographic Inspection
S10. Examination of Weld Preparation

S10.1 The method of performing the magnetic particle or liquid penetrant test shall be in accordance with Test Method **E165** or Guide **E709**.

S13. Hardness Test
S21. Heat Treatment Furnace Record
S22. Heat Treatment
S51. Mandatory Postweld Heat Treatment

S51.1 All castings with repair welds shall receive a mandatory thermal stress relief or complete reheat treatment in accordance with the qualified procedure after all weld repairs.

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A217/A217M – 08) that may impact the use of this standard. (Approved May 1, 2010.)

(I) Table 1 has been revised to limit the Columbium and Vanadium contents.

Committee A01 has identified the location of selected changes to this standard since the last issue (A217/A217M – 07) that may impact the use of this standard. (Approved Nov. 1, 2008.)

(I) Revised the introductory paragraph to the list of Supplementary Requirements to reference Specification **A985/A985M** for investment castings ordered to this specification.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).