

UNS S31803 / 1.4462 / F51

Technical Datasheet



Service. Quality. Value.

Duplex Stainless Steel

Product Description

Material to UNS S31803 (and the other specifications listed below) is described as a duplex stainless steel with a microstructure of 50:50 austenite and ferrite. The steel combines good mechanical strength (typically up to over 480 MPa yield strength) and ductility with moderate to good corrosion resistance in a variety of environments. By agreement, the alloy can be supplied with a PREN (Pitting Resistance Equivalent) at >34 which ensures that the resistance to pitting corrosion is as high as possible for this alloy grade. In addition, the steel offers good resistance to stress corrosion cracking. Ambient and sub-zero temperature notch ductility is good. These attributes mean that this duplex steel can be used successfully as an alternative to 300 series stainless steels in applications where higher mechanical strength / lower weight is required and / or resistance to stress corrosion cracking is needed.

Availability

Bar, forgings, sheet, plate, pipe, tube, closed die forgings, flanges and welding consumables.

Machinability / Welding

The machining and welding of this grade of duplex stainless steel presents no particular problems. Guidance notes are available upon request.

Typical Applications

Pumps, valves, chokes, Xmas trees, pipework / flanges, bolting, connectors & manifolds. In oil and gas industry. Equipment in brewing, power generation and chemical engineering.

Related Specifications

- UNS S31803 in various ASTM product form specifications
- EN 10088-3 1.4462 (Grade X2CrNiMoN22-5-3)
- NORSOK MDS D41 to D45, D47 & D48
- ASTM A182 F51
- NACE MR01-75 / ISO 15156

Chemical Composition (weight %)

Weight (%)	C	Mn	Si	S	P	Cr	Ni	Mo	N	*PREN
Min						21.0	4.5	2.5	0.10	33 - 34 Typical
Max	0.03	2.00	1.00	0.015	0.035	23.0	6.5	3.5	0.22	

* PREN = Cr % + 3.3Mo% + 16N%

Minimum Mechanical Properties at Room Temperature

(EN 10088-3 1.4547 max diameter 160mm - Solution Treated)

Ultimate Tensile Strength	650 – 880 MPa	(94 – 128 ksi)
0.2% Proof Strength	450 MPa	(65 ksi)
Elongation	25 %	
Hardness (Max)	270 HB	
Impact	100 J	(74 ft.lb)


Typical Properties

Density	7.8	kg/dm ³
Specific Thermal Capacity at 20°C	500	J.Kg ⁻¹ .K ⁻¹
Mean Coefficient of Thermal Expansion at 20 - 100°C	13.0	x 10 ⁻⁶ K ⁻¹
Thermal Conductivity at 20°C	15	W.m ⁻¹ .K ⁻¹
Electrical Resistivity at 20°C	0.80	Ω.mm ² .m ⁻¹
Modulus of Elasticity at 20°C	200	GPa
Magnetisable	No*	

UK Service Centres:

Smiths Belfast	02895 908 897	Smiths Leeds	0113 307 5167
Smiths Biggleswade	01767 604 704	Smiths London	020 7241 2430
Smiths Birmingham	0121 728 4940	Smiths Manchester	0161 794 8650
Smiths Bristol	0117 971 2800	Smiths Norwich	01603 789 878
Smiths Chelmsford	01245 466 664	Smiths Nottingham	0115 925 4801
Smiths Gateshead	0191 469 5428	Smiths Redruth	01209 315 512
Smiths Horsham	01403 261 981	Smiths Verwood	01202 824 347

Quality & Testing:



0845 527 3331

www.smithmetal.com



info@smithmetal.com

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.